



ANTI-SLIP SOLUTIONS
mail@heskins.us

www.heskins.us

05/13/2015

Heskins H3405 aqua-safe data sheet

Subject	Result	Test method
Back carrier	0.03" PVC	Caliper method
Type of adhesive	Modified solvent acrylic	N/A
Adhesive thickness	0.02"	N/A
Total thickness	0.03"	N/A
Initial tack (lb/l")	3.2	PSTC-16
Holding power	> 24 hour	PSTC-7
Peel adhesion (lb/l")	1.4	PSTC-1
Tensile strength (MD) (Ozf/'' ²)	120.4	ASTM D882A:1997
Elongation	199%	ASTM D882A:1997
Tear resistance (MD) (Ozf/inch)	5.36	ASTM D1004 : 1994-Die C
Dimensional stability(MD)	0%	ASTM D1593 : 1994
Temperature range	-22°F to +158°F	See notes below
Maximum size of production roll	47"x328ft	N/A

Coefficient of friction data

	Dry surface test result	Wet surface test result
Aqua-Safe	106 4S	31 4S

All the above data is for reference only.

©Heskins LLC 2016

